

DESCRIPTION

CR-3000 100% pure polyurea is a new generation of high-performance polyurea coating and is the result of six years of development and field testing. This chemical resistant coating provides high-ductility, allowing it to move with expanding and contracting surfaces. CR-3000 can be sprayed to any thickness in one application and returned to service in a matter of hours.

FEATURES

- An elastomer with chemical resistance; comparable to many epoxies.
- Self-priming in most instances, with strong adhesion.
- Return to service within hours not days (foot traffic 1 hour, vehicle traffic 4 hours).
- Typically applied in a single 'multi-pass' application.
- Eco-friendly, 100% solids, and no VOCs.

RECOMMENDED USES

- Primary and secondary containment.
- Steel tanks, concrete tanks, and silos.
- Barge and ship holds.
- Oil and gas pipelines.
- Waste water treatment facilities.
- Chemical transportation.
- Industrial flooring.
- Pulp and paper industry.
- Asbestos and lead encapsulation.

COLORS

CR-3000 is available in standard colors (Sand, Medium Grey, and Black). Custom colors available upon request. Note: CR-3000 is an aromatic polyurea. Therefore, with all aromatics, color change and superficial oxidation will occur. Aliphatic polyurea, urethane, polyaspartics, and other suitable topcoats can be used where long-term color stability and increased longevity in full sun exposure are of critical importance.

PACKAGING

This product sold in standard 110 gallon drum and 550 gallon tote sets. Available in other container sizes, contact sales representative for further information. Non-standard containers may require a longer lead time.

DRY PROPERTIES*

Tensile Strength ASTM D638	± 3,000 psi (21 MPa)
Elongation ASTM D638	± 100%
Hardness (Shore D) ASTM D2240-81	65 ± 5
Permeance ASTM D96-80	Perms-inch 0.007
Exposure Temperature**	-40° - +200°F (-45° - +93°C)

CURING SCHEDULE

Gel	± 4 sec
Tack Free	± 10 sec
Post Cure***	12 - 24 hour
Recoat	0 min - 6 hours

* All cured film properties are approximate since processing parameter, ad-mixture types, and quantities change physical properties of the cured elastomer. Elevated temperatures will accelerate the curing process and shorten the re-coat window.

** Tests performed in a dry, static environment.

** Complete polymerization to achieve final strength can take up to several days or weeks, depending on a variety of conditions or product type. All samples for above tests were force cured 48 hours or aged for more than three weeks. **It is recommended that the user perform their own independent testing.**

The samples for tests were sprayed with Graco HXP3P @ 2700 psi dynamic pressure at the gun. Proportioning machine primary heater and hose heat 170°F (77°C) Graco MP Fusion gun with 29/29 mixing chamber and .040 ceramtip.

TEST INFORMATION

Mandrel Bend Test ASTM D522-93a	Passed	Mandrel Size 1" Test Temp - 40°F (-40°C)
--	--------	---

IMMERSION

CHEMICAL	WEIGHT GAIN %	
Acetic 50%	4.88%	10 months
Diesel	0.05%	3 years
Gasoline (unleaded)	2.375%	17 months
Sulphuric Acid 14% Phosphoric Acid 30%	-0.43%	2 years
Jet Fuel JP-1,2,3	0.7%	5 years
Methanol	4.56%	19 months
Skydrol	8.25%	1 year
Sulphuric Acid 50%	3.075%	1 year

Immersion samples were 'free films' (6 sides exposed). In service, containment liners have only one side of liner exposed to reagents. To calculate approximate chemical absorption, we have divide the weight gain percentage in half as indicated on the chart. All tests performed at manufacture location at room temperature. Certified free film samples are available for immersion evaluation.

WET PROPERTIES

Solids by Volume	100%
Solids by Weight	100%
Volatile Organic Compounds	0 lbs/gal (0 g/l)
Theoretical Coverage DFT	100 sq. ft. @ 16 mils/gal
Weight per gallon (approx)	9.6 lbs. (4.35 kg)
Number of coats	1 or more
Mix Ratio	1 "A" : 1 "B"
Viscosity @77°F (25°C)	A: 650 ± 50 cPs B: 750 ± 50 cPs B @ 90°F 700 cPs
Shelf Life Unopened Containers @ 60 - 90°F (15 - 32°C)	6 Months

Minimum material/container temperature for application is 70°F (21°C).

MIXING & THINNING

Thoroughly agitate the "B" component of this product prior to application. Use a folding blade mixer, or equivalent equipment approved by Justrite. Install mixer through the extra air specific 2" bung hole provided on all "B" drums. Care must be taken not to cross contaminate the individual components with the mixing equipment; for best mixing results, supply the mixer with 25 cfm of air at 100 psi. Thinning is not required. Using any thinner may adversely affect product performance.

GENERAL APPLICATION INSTRUCTIONS

Apply CR-3000 only to clean, dry, sound, surfaces free of loose particles or other foreign matter. CR-3000 can be sprayed over a broad range of ambient and substrate temperatures. It is recommended that CR-3000 be sprayed in multi-directional (north/south - east/west) passes to ensure uniform thickness.

Contact Justrite technical service personnel for specific surface preparation for your application.

COMMON SUBSTRATES:

STEEL: 4-5 mil anchor profile is best for maximum adhesion and varies per application and conditions; adhere to proper SSPC standards.

WOOD: Clean, dry and sanded (to remove burrs, splinters, loose debris) for a smooth surface in which to apply polyurea onto. (It is recommended to prime wood and other porous surfaces before application of heated, fast-set polyureas to reduce pin holing)

CONCRETE: Prepare concrete in accordance with SSPC/NACE Standards and Concrete Prep Guide.

PREVIOUSLY APPLIED COATINGS: Justrite recommends UB™ (ULTRA BOND™) products over existing coatings that are past the recoat window and/or application over other coatings. Contact Justrite for additional information and to learn more about UB™ products.

On all above listed substrates and others, please contact Sales or Technical Support for more information specific to your application, including industry standards such as SSPC and NACE. **Adhesion tests are always recommended prior to application.**

PROCESSING EQUIPMENT & SETTINGS

MACHINES:

GRACO (Gusmer, Glass-craft)	<ul style="list-style-type: none"> A-XP1 E-10 HP E-XP1 E-XP2 H-20/35 Pro H-3500 HV 20/35 	<ul style="list-style-type: none"> H-XP2 H-XP3 Reactor2 E-XP2 Reactor2 E-XP2i Reactor2 H-XP2 Reactor2 H-XP3
PMC	<ul style="list-style-type: none"> PAX-25 PHX-2 PHX-25 	<ul style="list-style-type: none"> PHX-40 PMCA-20

GUNS:

GRACO (Gusmer, Glass-craft)	<ul style="list-style-type: none"> Fusion AP Fusion MP GAP Pro GX7-DI GX-8 Pro 	<ul style="list-style-type: none"> GX7-400 P2 P2 Elite P2 Elite "C" D7
PMC	<ul style="list-style-type: none"> AP-2 	
SPRAY FOAM EQUIP & MFG	<ul style="list-style-type: none"> Boss 	

- Standard 1:1 ratio, heated, plural-component equipment developing a minimum of 2500 psi (17.24 MPa) dynamic pressure at the gun with heating capabilities to 170°F (77°C) will adequately spray CR-3000.

- Machines capable of producing a higher dynamic psi may be required depending on the service environment the CR-3000 will be exposed to. Consult Justrite technical service personnel for additional information.
- Proportioning machine primary heater temperature 160-170°F (71-77°C).
- Hose temperature 160-170°F (71-77°C). A hose thermometer inserted under the insulation near the gun should read a minimum of 145-155°F (63-68°C)
- Physical properties will be enhanced when sprayed at higher pressure (3000 psi or more); utilizing an impingement mix gun such as MP Fusion or GX7-DI gun.
- Do not use mixing chambers with output greater than 1.5 gallons per minute. Consult technical service personnel for additional information.

If you own a machine that is not listed above please contact your Justrite representative for information and instructions.

PARAMETERS & LIMITATIONS

- CR-3000 is for professional use only. User must be proficient in the application of CR-3000 and use of the high pressure heated plural component equipment used to apply it.
- CR-3000 must be stored at temperatures between 60–90°F (15–32°C).
- Liquid temperature in containers/drums during application 70–100°F (21–38°C).
- Apply CR-3000 when surface and air temperatures are above 40°F (5°C) and the surface temperature is at least 5°F (3°C) above dew point and rising.
- Minimum material/container temperature for spray application is 70°F (21°C).
- Avoid moisture contamination in containers. Containers should not be resealed if contamination is suspected. CO₂ created pressure can develop. Do not attempt to use contaminated material.
- Undried air exposed to liquid components will reduce physical properties of the cured coating.

Note: The material supplied is a two component system (component “A”/component “B”, which is used to formulate this product. The quality and characteristics of the finished polymer is determined by the mixture and application of the two components by the person applying the polymers.

For the most up to date technical data sheet and/or safety data sheet contact Justrite.

GENERAL SAFETY, TOXICITY, & HEALTH

Safety Data Sheets are available for this coating material. Any individual who may come in contact with these products should read and understand the S.D.S. **CHEMTREC EMERGENCY NUMBER 1-800-424-9300**

WARNING: Contact with skin or inhalation of vapors may cause an allergic reaction. Avoid eye contact with the liquid or spray mist. Hypersensitive persons should wear protective clothes, gloves and use protective cream on face, hands and exposed areas.

CLEAN UP: Use DPM or NMP.

CONTAMINATION: Avoid moisture contamination in containers. Containers should not be resealed if contamination is suspected, CO₂ created pressure can develop. Do not attempt to use contaminated material.

EYE PROTECTION: Safety eye wear complying with an approved standard should be used when a risk assessment indicates this is necessary to avoid exposure to liquid splashes, mists, or dusts. If contact is possible, the following protection should be worn, unless the assessment indicates a higher degree of protection: chemical splash goggles and/or face shield.

SKIN PROTECTION: Personal protective equipment for the body should be selected based on the task being performed; the risks involved, and should be approved by an industrial hygiene specialist before handling this product. Chemical resistant gloves complying with applicable health and safety standards shall be worn when handling this product. Cover as much of the exposed skin area as possible with appropriate clothing. Refer to safety data sheet (SDS).

RESPIRATORY PROTECTION: Harmful if inhaled and may cause allergy or asthma symptoms. Ensure adequate ventilation. If the respirator is the sole means of protection, use a full-face supplied respirator. Use respirators and components tested and approved under appropriate government standards such as OSHA 29CFR 1910.134, NIOSH (US), or CEN (EU). Consider the application and environmental concentrations when deciding if additional protective measures are necessary.

INGESTION: Do not take internally. It is believed that ingestion of polymeric isocyanates would not be fatal to humans, but may cause inflammation of mouth and stomach tissue.



WARRANTY & DISCLAIMER

Justrite has no role in the manufacture of the finished polymer other than to supply its two components. It is vital that the person applying this product understands the product, and is fully trained and certified in the use of plural-component equipment. Justrite warrants only that the two components of this product shall conform to the technical specifications published in the product literature. The quality and fitness of the product are dependent upon the proper mixture and application of the components by the applicator. There are no warranties that extend beyond the description on the face of this instrument. Failure to apply the product within the parameters stated on this document shall void the warranty. **JUSTRITE MAKES NO WARRANTY OF MERCHANTABILITY OF THE PRODUCT OR OF FITNESS OF THE PRODUCT FOR ANY PARTICULAR PURPOSE.** Justrite makes no warranty as to the quality of any product modified, supplemented, tinted, or altered in any way after it leaves the manufacturing plant. Justrite does not warrant that this product is suitable for use as a liner for potable water containers. Use of this product in a potable water container could be hazardous to health if it is improperly processed or applied. The liability of Justrite for any nonconformity of the product to its technical specifications shall be limited to replacement of the product. The sole exclusive remedy of buyer, which is to have Justrite replace any nonconforming product at no cost to buyer, is conditioned upon buyer notifying Justrite or its distributor in writing of such defect within thirty days of the discovery of such defect. Justrite shall not be liable for any direct, incidental, or consequential damages resulting from any breach of warranty. The data presented herein is intended for professional applicators or those persons who purchase or utilize this product in the normal course of their business. The potential user must perform any pertinent tests in order to determine the product's performance and suitability in the intended application, since final determination of fitness of the product for any particular use is the responsibility of the buyer. The aforementioned data on this product is to be used as a guide and is subject to change without notice. The information herein is believed to be reliable, but unknown risks may be present. Justrite makes no warranties, expressed or implied, including patent warranties or warranties of merchantability or fitness of use, with respect to products or information set forth herein. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent. Accordingly, the buyer assumes all risks whatsoever as to the use of these materials and buyer's exclusive remedy as to any breach of warranty, negligence, or other claim shall be limited to the purchase price of the materials. Failure to adhere to any recommended procedures shall relieve Justrite of all liability with respect to the materials and the use thereof.

CONTACT US

Basic Concepts Inc. dba Justrite
1310 Harris Bridge Rd, Anderson, SC 29621
813-659-3512